

# **Product Manual(TDS)**

# **Urethane acrylate BW 8070**

### **Product introduction**

BW 8070 a solvent-based aliphatic polyurethane acrylate. It has the characteristics of excellent foil stamping, good additive color, good metal adhesion, etc. It is mainly used in cosmetic package vacuum plating top coat and plastic UV varnish, shows good interlayer adhesion after adding color essence.

#### **Product characteristics**

Functional	3.2	Hardness	-
Active Ingredient (%)	-	Proportion (25°C)	1.06
Appearance (25°C)	Clear transparent liquid	Shrinkage(%)	-
Viscosity (cps at 25°C)	1300-2200	Refractive Index(n <sub>d</sub> at 25°C)	1.48
Color (APHA)	≤60	Elongation At Break (%)	-
Acid Value (mg KOH/g)	6.0-8.0	Tensile Strength (MPa)	-

- Good coloring;
- Good resistance to boiling;
- Good adhesion to aluminum;
- Excellent bronzing on film surface;

## **Applications**

It is used in vacuum-plated topcoats for cosmetics primer and UV plastic varnish, UV plastic colored paint.

#### **Packaging**

- In 20 kg plastic drums
- In 200 kg metal drums

# **Storage**

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (up to 45°C);

It is especially suggested that the above data and suggestions are based on experimental data, but due to the uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.

We recommend that customers choose our products and adopt them. Determine their applicability before making our recommendations.

A 广州市番禺区番禺大道北555号天安节能科技园产业大厦1座904

904. NO. 1 Building, Tianan Hi- tech Ecological Park.No.555 panyu road North, Panyu,Guangzhou

T 020- 3107 4363 F 020- 3107 4309 E contact@bawo-chem.com W www.bawo-chem.com Factory: Guangdong · Yingde





