



## Product Manual(TDS)

### Urethane acrylate BW 300B

#### Product introduction

**BW 300B** is a large molecular weight tough aliphatic polyurethane acrylate. It is especially suitable for plastic paints (e.g. vacuum plating primer for cosmetics and cell phones), resilient parquet paints, and UV inks, etc. It provides excellent toughness, good interlayer adhesion, good reaction speed, and resistance to boiling water for the coating film.

#### Product characteristics

Functional	2	Hardness	-
Active Ingredient (%)	100%	Proportion (25°C)	1.12
Appearance (25°C)	Transparent clear liquid	Shrinkage(%)	-
Viscosity (cps at 60°C)	50000-75000	Refractive Index( $n_d$ at 25°C)	1.49
Color (APHA)	$\leq 80$	Elongation At Break (%)	178
Acid Value (mg KOH/g)	$\leq 5$	Tensile Strength (MPa)	12

- Fast curing speed;
- Excellent adhesion;
- Good toughness;
- Low shrinkage;

#### Applications

- It is used in UV ink, UV transfer adhesive, UV resilient parquet, vacuum plating primer, UV furniture coating and other fields.

#### Packaging

- In 20 kg plastic drums
- In 200 kg metal drums

#### Storage

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (Maximum temperature 45°C);

**It is especially suggested that the above data and suggestions are based on experimental data, but due to the uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.**

**We recommend that customers choose our products and adopt them. Determine their applicability before making our recommendations.**

