



## Product Manual(TDS)

### Urethane acrylate BW 8096

#### Product introduction

**BW 8096** is an aliphatic polyurethane acrylate with good toughness and abrasion resistance. It is particularly suitable for UV-hardened coatings, plastic paints, furniture and parquet paints and inks. It provides high scratch resistance, excellent toughness and abrasion resistance.

#### Product characteristics

Functional	9	Hardness	-
Active Ingredient (%)	100%	Proportion (25°C)	1.19
Appearance (25°C)	Clear transparent liquid	Shrinkage(%)	-
Viscosity (cps at 40°C)	50000-75000	Refractive Index(nd at 25°C)	1.50
Color (APHA)	≤60	Elongation At Break (%)	-
Acid Value (mg KOH/g)	≤1	Tensile Strength (MPa)	-

- Good toughness and hardness;
- Excellent abrasion resistance;
- Fast curing speed;
- Good fullness;

#### Applications

- It is used in vacuum plating, UV coating of plastics, UV-hardening coatings, UV lacquers for furniture and parquet, UV inks, etc.

#### Packaging

- In 20 kg plastic drums
- In 200 kg metal drums

#### Storage

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (up to 45°C);

**It is especially suggested that the above data and suggestions are based on experimental data, but due to the uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.**

**We recommend that customers choose our products and adopt them. Determine their applicability before making our recommendations.**

